



**Technical Data Sheet** 

# FRICTO LITHIUM GREASE EP

### PRODUCT DESCRIPTION:

Fricto Lithium EP is a Lithium thickened lubricating grease formulated with mineral base oil and improved with extreme pressure (EP) additives to lubricate and protect even in heavy loaded circumstances. Mechanically very stable and easily pumpable due to its smooth consistency.

### APPLICATION:

- Fricto Lithium EP-000 and EP-00 are particularly suitable for the lubrication of enclosed gears and bearings in poorly sealed gear cases on most underground mining machinery with the exception of electric motor gearings.
- Fricto Lithium EP-0 and EP-1 provide good low temperature pumpability and are suitable for centralised lubrication systems
  and other applications where low temperature performance is required.
- Fricto Lithium EP-2 is recommended for multipurpose applications in antifriction and plain bearings, bushings and pins under normal operating conditions.
- Fricto Lithium EP-3 is is a stiffer NLGI grade 3 grease recommended for applications where maximum protection against
  penetration of water or solid contaminants is required.

### FEATURES & BENEFITS:

- · Reduced wear under heavy or shock loading
- · Protection against rust and corrosion
- Resistance to water washout
- · Extended bearing life potential
- · Good pumpability in centralised systems
- · Effective leakage control

MEETS OR EXCEEDS THE REQUIREMENTS OF:	NLGI 000	NLGI 00	NLGI 0	NLGI 1	NLGI 2	NLGI 3
DIN 51825	-	-	-	KP1K-20	KP2K-20	KP3K-20
DIN 51826	GP000G-20	GP00G-20	GP0G-20	-	-	-

### TYPICAL PROPERTIES:

TEST	ASTM METHOD	FRICTO LITHIUM EP							
		NLGI 000	NLGI 00	NLGI 0	NLGI 1	NLGI 2	NLGI 3		
Thickener Type		Lithium							
Color		Light Brown							
Texture		Smooth							
Worked Penetration @ 25°C, 60 Strokes	D-217	460	415	370	325	280	235		
Dropping Point, °C	D-2265	>160	>160	>160	180	190	190		
Timken EP Test, OK Load, Ibs	D-2509	40	40	40	40	40	40		
4-Ball Wear, Scar, mm	D-2266	0.4	0.5	0.4	0.4	0.4	0.4		
4-Ball Weld Load, Kg	D-2596	250	250	250	250	250	250		
Base Oil Viscosity @ 40°C, cSt	D-445	320	160	160	160	160	160		
Operating Temperature Range, °C		-30 to 110	-30 to 130						



## **AUTOMOTIVE/INDUSTRIAL GREASES**



**Technical Data Sheet** 

### HEALTH & SAFETY, ENVIRONMENT:

Prolonged and repeated contact with oil may cause skin disorders. Avoid contact. Wash immediately with soap and water. Do not discharge used oil in to drains or the environment. Dispose to an authorized used oil collection point. For further Information on Safety Guidelines please refer to MSDS available on our website www.lubrex.net

### HEALTH & SAFETY:

This product is not likely to present any significant health or safety hazards when properly used in the recommended application and good standards of personal hygiene are maintained. Reference is made to the Safety Data Sheet (SDS) which is available on request via your local sales office or via the internet www.lubrex.net

### PROTECT THE ENVIRONMENT

Take used oil to an authorized collection point. Comply with local regulation. Do not discharge into drains, soil or water.

### STORAGE:

We recommend to store all packages under cover. In case outside storage is unavoidable, drums should be laid horizontally to avoid the possible ingress of water and damage to drum markings. Products should never be stored above 60°C, exposed to hot sun or freezing conditions.

™ Trademark of LUBREX, registered in various countries © 2005

All statements, information and data presented herein are believed to be accurate and reliable, but are not to be taken as a guarantee, an express warranty or an implied warranty of merchantability or fitness for a particular purpose, or representation, express or implied, for which LUBREX and its affiliates assume legal responsibility.